TWO-COMPONENT TEXTURED COATING
RTB-1324-T (A&B COMPONENTS)

RTB-1324-T offers excellent adhesion, outdoor stability, durability, and chemical, weather and ultra-violet radiation resistances; leaving behind a fine textured surface.

USES AND SUITABALE PRIMERS

Recommended Uses	Finish Textured coating for protective coating systems, maintenance operations and primed metal surfaces.
Suitable Primers	Epoxy primers and intermediate epoxy coatings.

CHEMICAL COMPOSITION

Type of Binder	Acrylic Polyol	Solid Content After Mixing	62 ± 1% By Weight
Number of Component(s)	2 Components		40 ± 3% By Volume
Curing Mechanism	Chemical Reaction	Flash Point	28°C (82°F)

PHYSICAL PROPERTIES

Finish	Semi flat
Colour	Jet Black (RAL-9005) | This coating is also available in other colours
Specific Gravity After Mixing	1.35 ± 0.05 gr/cm³

APPLICATION DETAILS

Surface Preparation: All oil, grease, dirt and other contaminants must be removed from the surface. Sandblast according to Swedish Standard (SIS 5900)Sa. 2 ½ and treatment with an epoxy primer and intermediate coating is recommended.

Mixing Ratio: Component A: 100 Parts by weight Component B: 25 Parts by weight

Mixing Instructions: Mix component A thoroughly with a suitable mixer, then add component B slowly and mix well for 5 minutes. Keep the mixture for 10 additional minutes prior to thinning down to allow for the pre-reaction time. Do not thin down each component separately.

Pot Life: 6 Hours at 25°C

Theoretical Consumption: 200 gr/m² @ 60 Microns DFT

Paint Application

Methods	Airless Spray	Air Spray	Brush	Roller
Nozzle Size	0.021" – 0.029"	1.80 mm	---	---
Pump Ratio	1 / 68	---	---	---
Air Pressure	4 – 6 Bar	3 – 5 Bar	---	---
Thinning	7 – 10% T-849	15 – 20% T-849	3 – 5% T-849	3 – 5% T-849

Film Thickness

	Recommended	Minimum	Maximum
Wet Film Thickness (µm)	150	85	250
Dry Film Thickness (µm)	60	35	100

Drying Time@25°C

Dust Free Time	Tack Free Time	Dry to Handle	Fully Cured	Recoating Interval
20 – 30 Minutes	45 – 60 Minutes	2 – 3 Hours	3-5 Days	Min. 16 Hours Max. Not Limited

**Drying time calculated at 25°C according to ASTM test method D-1640 for 100 µm WFT*

Application Limits

Relative Humidity	Min. ---	Max. 80%
Temperature	Min. +5°C	Max. +40°C
Substrate Temperature*	Min. +5°C	Max. +45°C

**Please note that the substrate temperature should be at least 5°C above the dew point*

Recommendations: -Should the recoating interval have expired, please refer to the procedures outlined in the Ronass Instruction Leaflet.
-Clean tools thoroughly before and immediately after use with cleaning solvent T-111 or T-849.

PACKING, STORAGE AND SAFETY

Packing: Component A (Base): 20 Litres Containers (20 kgs. Net) Component B(Hardener): 1Litres Containers (0.750 kgs. Net)

Storage Conditions: To be stored in cool and dry conditions in original sealed containers.

Shelf Life: At least 18 months after delivery in original sealed containers and proper storage conditions with temperature of 25°C.

Safety: This product contains organic solvents and flammable materials. Keep away from sparks, fires, electrical cables and equipments,direct sunshine and out of children's reach.

Protect skin, eyes, and avoid prolonged breathing of solvent vapor during application. Use with adequate ventilation.