RONASS ZINC CHROMATE PRIMER

RTB-954

Special one-component primer based on chlorinated Rubber Resin with excellent adhesion and anti-corrosive properties.

USES AND SUITABALE TOP-COATS

Recommended Uses	First or single coating system for steel structures and maintenance operations.
Suitable Top-Coats	Alkyd paints, chlorinated rubber coatings and synthetic enamels.

CHEMICAL COMPOSITION

Type of Binder	Chlorinated Rubber Binders.	Solid Content	70 ± 1% By Weight
Number of Component(s)	1 Component		50 ± 2% By Volume
Curing Mechanism	Solvent Evaporation and Oxidation		
Main Pigment(s)	Zinc Chromate Pigment.	Flash Point	28°C (82°F)

PHYSICAL PROPERTIES

Finish	Semi flat
Colour	Reed Green (RAL-6013)
Specific Gravity	1.40 ± 0.05 gr/cm³

APPLICATION DETAILS

Surface Preparation: All oil, grease, dirt and other contaminants must be removed from the surface. Wire brush or sandblast according to the Swedish Standard (SIS 5900). Sa 2 is recommended.

Theoretical Consumption: 140 gr/m² @ 50 Microns DFT

Paint Application

Methods	Airless Spray	Air Spray	Brush	Roller
Nozzle Size	0.011" – 0.015"	1.80 mm	---	---
Pump Ratio	1 / 28	---	---	---
Air Pressure	4 – 6 Bar	3 – 5 Bar	---	---
Thinning	5 – 10% T-611	10 – 20% T-611	3 – 5% T-611	3 – 5% T-611

Film Thickness

	Recommended	Minimum	Maximum
Wet Film Thickness (µm)	120	80	160
Dry Film Thickness (µm)	60	40	80

Drying Time@25°C

Dust Free Time	Tack Free Time	Dry to Handle	Fully Cured	Recoating Interval
30 – 60 Minutes	2 – 3 Hours	16 – 24 Hours	7 Days	Min. 16 Hours Max. Not Limited

**Drying time calculated at 25°C according to ASTM test method D-1640 for 100 µm WFT*

Application Limits

Relative Humidity	Min. ---	Max. 80%
Temperature	Min. +5°C	Max. +40°C
Substrate Temperature*	Min. +5°C	Max. +45°C

**Please note that the substrate temperature should be at least 5°C above the dew point*

Recommendations: Clean tools thoroughly before and immediately after use with cleaning solvent T-111 or T-611.

PACKING, STORAGE AND SAFETY

Packing: 20 Litres Containers (25 kgs. Net)

Storage Conditions: To be stored in cool and dry conditions in original sealed containers.

Shelf Life: At least 12 months after delivery in original sealed containers and proper storage conditions with temperature of 25°C.

Safety: This product contains organic solvents and flammable materials. Keep away from sparks, fires, electrical cables and equipments,, direct sunshine and out of children's reach.

Protect skin, eyes, and avoid prolonged breathing of solvent vapor during application. Use with adequate ventilation.